



CenFloHDPE

*Flexible Polyethylene Pipe and Tubing
Produced from only the finest virgin PE Resins*



Effective January, 2024
Supersedes January 2019

HDPE 4710 — ASTM D2239

Chlorine resistance: CC3 per ASTM F2263

ASTM D2239

SIDR 11.5 | 160 PSI

Dimensions	SKU	Avg OD (in)	ID (in)	Min Wall (in)	Wt / Ft (lbs)
1/2"	FL471600050	.742	.622	.060	.057
3/4"	FL471600075	.968	.824	.072	.090
1"	FL471600100	1.231	1.049	.091	.143
1 1/4"	FL471600125	1.620	1.380	.120	.246
1 1/2"	FL471600150	1.890	1.610	.140	.335
2"	FL471600200	2.427	2.067	.180	.544

Centennial CenFlo HDPE 160PSI @ 73°F SIDR 11.5 ASTM D 2239 NSF-pw U.P. Code PE 4710

SIDR 9 | 200 PSI

Dimensions	SKU	Avg OD (in)	ID (in)	Min Wall (in)	Wt / Ft (lbs)
3/4"	FL472000075	1.008	.824	.092	.116
1"	FL472000100	1.283	1.049	.117	.186
1 1/4"	FL472000125	1.686	1.380	.153	.320
1 1/2"	FL472000150	1.968	1.610	.179	.430
2"	FL472000200	2.527	2.067	.230	.710

Centennial CenFlo HDPE 200PSI @ 73°F SIDR 9 ASTM D 2239 NSF-pw U.P. Code PE 4710 CC3

SIDR 7 | 250 PSI

Dimensions	SKU	Avg OD (in)	ID (in)	Min Wall (in)	Wt / Ft (lbs)
3/4"	FL472500075	1.060	.824	.118	.152
1"	FL472500100	1.349	1.049	.150	.246
1 1/4"	FL472500125	1.774	1.380	.197	.424
1 1/2"	FL472500150	2.070	1.610	.230	.578
2"	FL472500200	2.657	2.067	.295	.952

Centennial CenFlo HDPE 250PSI @ 73°F SIDR 7 ASTM D 2239 NSF-pw U.P. Code PE 4710 CC3

Note: For stocking coil lengths, please see centennialplastics.com

ISO 9001:2015
Certified



Scan here
to learn
more about
our Potable
Water Pipe

ESSENTIAL LINKS (click link for website or to download file)

- » PE Handbook
- » Plastic Pipe Design Calculator
- » Temperature Effects on Centennial Poly (HDPE App)
- » CenFlo Stocking Coil Lengths
- » Chemical Resistance of Plastic Piping Materials
- » Weatherability of Thermoplastic Piping Systems

CERTIFICATIONS & REFERENCES

- » **ASTM D2239** — Specification covers the testing, marking, in-plant QC, and annual testing requirements for PE pipe intended for non-potable water piping systems and meeting the dimensional requirements of ASTM D2239.
- » **NSF/ANSI 14** — Plastics Piping System Components and Related Materials establishes the minimum physical, performance and health effects requirements for plastics piping system components and related materials.
- » **NSF/ANSI/CAN 61** — Drinking Water System Components - Health Effects
- » **ASTM D3350** — Centennial PE3608 meets thermal stability, brittleness temperature and elongation at break requirements as outlined in this specification.
- » **SIDR 11.5, SIDR 9 and SIDR 7** are suitable for connections with insert fittings and clamps. SIDR 7 is suitable for compression fittings with pipe stiffeners, PAC joints, etc. *Refer to fitting manufacturers for proper installation.*
- » **CenFlo** is tested and certified to NSF/ANSI Standard 14 and 61.
- » **CenFlo** is Certified to NSF/ANSI 372 and conforms with the lead content requirements for “lead free” plumbing as defined by California, Vermont, Maryland, and Louisiana state laws and the U.S. Safe Drinking Water Act.
- » **Build America, Buy America (BABA Act)** — We proudly hold a BABA Act certification.
- » **§ CenFlo HDPE** is certified to the Uniform Plumbing Code™
- » **Centennial Plastics follows Proposition 65 – www.P65Warnings.ca.gov**
Our products in their finished form do not require a California Proposition 65 warning label.



centennialplastics.com

